



Artists at Work: Ted Sawyer

PRODUCTS USED

Sheet Glass

- Clear Tekta, 6 mm ([001100-0680](#))

Powder

- French Vanilla Opalescent ([000137-0008](#))
- Steel Blue Opalescent ([000146-0008](#))
- Deep Plum ([001105-0008](#))
- Turquoise ([001116-0008](#))
- Sienna ([001119-0008](#))
- Red ([001122-0008](#))
- Orange ([001125-0008](#))

Other Supplies

- Bullseye GlasTac, 4 oz Bottle ([008234](#))
- Bullseye ThinFire Shelf Paper
- Condiment cups
- Disposable Particulate Respirator N100 ([008261](#))
- Frit Sifter, Powder ([008237](#))
- Sharpie
- Syringe

FIRING SCHEDULES

Initial Firing

	RATE	TEMPERATURE	HOLD
1	100° F (56° C)	200° F (93° C)	1:00
2	80° F (44° C)	1000° F (538° C)	:10
3	560° F (311° C)	1280° F (693° C)	:10
4	AFAP	900° F (482° C)	1:00
5	100° F (56° C)	700° F (371° C)	:00
6	AFAP	70° F (21° C)	:00

More Conservative Firing Schedule

	RATE	TEMPERATURE	HOLD
1	100° F (56° C)	200° F (93° C)	1:00
2	80° F (44° C)	1000° F (538° C)	:10
3	560° F (311° C)	1280° F (693° C)	:10
4	AFAP	900° F (482° C)	2:00
5	50° F (28° C)	700° F (371° C)	:00
6	AFAP	70° F (21° C)	:00

* AS FAST AS POSSIBLE