

PRODUCTS FOR THIS PROJECT

Light Sky Blue Transparent (001414-0030-F)
Black Opalescent (000100-0030-F)
Slumping Mold (008924)
Toyo Self-Oiling Cutter (007010)
80, 220, and 400 grit sand
Float glass

COLDWORKING GRITS

Silicon Carbide, 80 Grit (7241)
Silicon Carbide, 120 Grit (7248)
Silicon Carbide, 220 Grit (7242)
Silicon Carbide, 400 Grit (7243)
Silicon Carbide, 800 Grit (7244)

FIRING SCHEDULES FOR THIS PROJECT

Slump Firing

	RATE	TEMPERATURE	HOLD
1	300°F (222°C)	1180°F (638°C)	:10
2	AFAP	900°F (482°C)	1:00
3	100°F (56°C)	700°F (371°C)	:00
4	AFAP	70°F (21°C)	:00