

PRODUCTS FOR THIS PROJECT

Cobalt Blue Opalescent sheet (000114-0030-F)
Orange Transparent sheet (001125-0030-F)
Tekta Clear sheet (001100-0680-F)
Silver foil (7217)
Black Opalescent sheet (000100-0030-F)
White Opalescent sheet (000113-0030-F)
Clear Transparent sheet (001101-0031-F)
Clear Transparent billet (001101-0065-F)
Erbium Pink Tint sheet (001821-0030-F)
Deep Royal Blue Transparent sheet (001114-0030-F)
Crystal Clear Transparent billet (001401-0065-F)
Polarizing Film (8270, 8271)

FIRING SCHEDULES FOR THIS PROJECT

Firing schedule with slower initial heating rate and a more conservative cooldown

	RATE	TEMPERATURE	HOLD
1	200°F (111°C)	1225°F (663°C)	1:30
2	600°F (333°C)	1490°F (810°C)	:10
3	AFAP	900°F (482°C)	1:00
4	100°F (56°C)	700°F (371°C)	:00
5	AFAP	70°F (21°C)	:00